## Ready-Mix Joint Compound

Freeman Products Ready-Mix Joint Compound is formulated for embedding drywall tape, finishing joints, fasteners, corner beads and drywall trims. Ready-Mix Joint Compound may also be used for filling, leveling and finishing coats, skim-coating entire wall surface and use as a texture. Freeman Products Ready-Mix Joint Compounds include: All Purpose, Freeflow, Topping, and Lite formulations.

**Delivery and Storage of Materials:** All materials shall be delivered in the manufacturer's original, unopened, undamaged containers with identification labels intact. Store material in a protected area not exposed to extremes in temperature. Do not store in direct sunlight. Keep product from freezing.

**Environmental Conditions:** During application of gypsum board, joint finishing and decorating a constant temperature above 50 F and below 100 F must be maintained before, during and after installation. Provide adequate ventilation, allow product dry completely.

**Mixing:** Stir material thoroughly. If a thinner viscosity is required use only clean potable water. Avoid over mixing and over thinning. Do not mix with any other product.

**Application:** Apply Ready-Mix Texture with brush, roller, airless-sprayer, piston or stator-type pump. Allow first coat to dry completely before applying additional coats. Maintain a minimum of 50 F air and surface temperature during application.

**Coverage:** Approximately 8-9 gal per 1000 sq/ft for Lite. All Purpose and Topping 140lbs per 1000 sq/ft. Freeflow about 9 to 9.5 gal/ 1000 sq/ft. Depending on job conditions

**Cleanup:** Clean all tools, equipment and skin with soapy water and rinse with clean water. Clean all drips and spills immediately with a damp cloth.

**Sanding:** If sanding is required, use a NIOSH/MSHA approved respirator.

**Decorating:** When painting or decorating follow manufacturer's instructions.



**Compliance with Standards:** Freeman Products, Inctesting complies with ASTM C474-13 Standard Test Methods for Joint Treatment Materials for Gypsum Board Construction.

When applied in accordance with Freeman Products, Inc. application guidelines and ASTM C840-13 Standard Specification for Application and Finishing of Gypsum Board, Freeman Joint Compounds comply with the following standards:

ASTM C475/C475M-12 Standard Specification for Joint Compound and Joint Tape for Finishing Gypsum Board

ASTM C1396/C1396M-14a Standard Specification for Gypsum Board

**Material:** Vinyl Acetate based texture.

**Freezing Sensitivity:** Protect material from freezing during storage, application and until completely dry.

**Storage:** Rotate stock, shelf life six (6) months from date of manufacture.

**Packaging:** Available in 5 gallon pail or 3.5 gal box.

## DO NOT TAKE INTERNALLY. KEEP OUT OF REACH OF CHILDREN

## **Submittal Approval**

Job Name:	
Contractor:	Date:

For a complete copy of warranty information contact: **Freeman Products, Inc. 1-800-364-2763**